



Ockwells PVC Easi-Peel Low Tack Tape

Applications

Properties	Unit	Value
Total thickness	mm	0.15±0.015
Backing Thickness	mm	0.135±0.013
Glue thickness	mm	0.015±0.015
Adhesive	-	Rubber
Elongation	%	≥ 130
Peel adhesion	N/cm	≥ 1.6
Tensile strength	N/cm	≥ 20
Application temperature	°C	0 ~50
Heat resistance	°C/min	-12~80
Storage temperature	°C	Normal room temp.
Shelf life	Month	24

1. The data above is typical of PVC Tapes and subject to change without notice.
2. The product should be stored at room temperature and kept from moisture and heat source.
3. For interior use the product is UV Resistant for up to 14 days.
For exterior use the product is UV Resistant for up to 5 days.
4. It is essential as with all pressure-sensitive tapes, that the surface to which the tape is applied must be clean, dry, and free of grease and oil.
5. Dimension Tolerance PVC Tapes:
Thick: ±0.015mm for thickness up to and including 0.20mm, ±0.03mm for greater thickness.
Width: ±1mm for widths up to and including 19mm, ±1.5mm for greater widths.
Length: ±30cm for lengths up to and including 25m, ±50cm for greater lengths within 100m.

Due to the different properties and characteristics of material surfaces, the purchaser and or user should test the suitability of the tape in an unexposed area in order to satisfy themselves that the tape is suitable for their requirements.

If unsure of the products suitability - DO NOT USE!

NEWBURY

Unit 6, Transigo,
Gables Way, Thatcham,
Berkshire RG19 4ZA

T: 01635 876336
sales@ockwells.com

WARRINGTON

Unit 12, Cameron Court,
Winwick Quay,
Warrington WA2 8RE

T: 01925 820003
sales.warrington@ockwells.com

GLASGOW

Unit 2, 45 Mackellan Street,
Kinning Parkway Estate,
Glasgow G41 1RR

T: 0141 427 3366
sales.glasgow@ockwells.com

EAST LONDON

Unit E1, Thames View Business Centre
Fairview Industrial Park
Rainham RM13 8BT

T: 020 7473 8770
sales.rainham@ockwells.com