



Ockwells Ultra Low Tack Tape

Applications

Temporary protection of surfaces including brushed aluminium, ground or deep drawing stainless steel, matt painted coils and PVC profiles/plates & wood.

Do not use on copper, brass and copper containing alloys.

Not suitable for protection against, corrosion, humidity or chemical solvents

Technical Data

Film Type:

Average Thickness (A.F.E.R.A. 4006):

Colour:

Adhesive Type:

Melting Point:

Adhesion to Steel (A.F.E.R.A 4001)

Longitudinal Tensile Strength

A.F.E.R.A. 4004

Transversal Tensile Strength

(A.F.E.R.A. 4004)

Longitudinal Max. Elongation

(A.F.E.R.A.4005)

Transversal Max Elongation

(A.F.E.R.A. 4005)

Unit

Polyethylene (LDPE)

Micron 80

Black

Rubber

80°C

cN/cm 105

daN/cm >1.55

daN/cm >1.2

% >350

% >570

Storage & Utilisation

The tape can be stored for 6months in dry conditions in its original packaging.

Do not expose materials protected with black or black/white tape to exterior conditions for more than 6months.

Due to the different properties and characteristics of material surfaces, the purchaser and or user should test the suitability of the tape in an unexposed area in order to satisfy themselves that the tape is suitable for their requirements.

If unsure of the products suitability - DO NOT USE!

These properties are the Manufacturers' typical values based on the average of several tests. As the installation and handling of this product is beyond our control the user must ensure that the product is suitable for the application. Ockwells cannot accept responsibility for any loss or damage that may occur either directly or indirectly using this product. Ockwells also holds the right to change specification data without prior notice

NEWBURY

01635 876336
sales@ockwells.co.uk

WARRINGTON

01925 820003
sales.warrington@ockwells.co.uk

GLASGOW

0141 427 3366
sales.glasgow@ockwells.co.uk

EAST LONDON

020 7473 8770
sales.eastlondon@ockwells.co.uk