



Ockwells Ultra Low Tack Tape

Applications

Temporary protection of surfaces including brushed aluminium, ground or deep drawing stainless steel, matt painted coils and PVC profiles/plates & wood.

Do not use on copper, brass and copper containing alloys.

Not suitable for protection against, corrosion, humidity or chemical solvents

Technical Data

Film Type:

Average Thickness (A.F.E.R.A. 4006):

Colour:

Adhesive Type:

Melting Point:

Adhesion to Steel (A.F.E.R.A. 4001)

Longitudinal Tensile Strength

A.F.E.R.A. 4004

Transversal Tensile Strength

(A.F.E.R.A. 4004)

Longitudinal Max. Elongation

(A.F.E.R.A. 4005)

Transversal Max Elongation

(A.F.E.R.A. 4005)

Unit

Polyethylene (LDPE)

Micron 80

Black

Rubber

80°C

cN/cm 105

daN/cm >1.55

daN/cm >1.2

% >350

% >570

Storage & Utilisation

The tape can be stored for 6months in dry conditions in its original packaging.

Do not expose materials protected with black or black/white tape to exterior conditions for more than 6months.

Due to the different properties and characteristics of material surfaces, the purchaser and or user should test the suitability of the tape in an unexposed area in order to satisfy themselves that the tape is suitable for their requirements.

If unsure of the products suitability - DO NOT USE!

NEWBURY

Unit 6, Transigo,
Gables Way, Thatcham,
Berkshire RG19 4ZA

T: 01635 876336

sales@ockwells.com

WARRINGTON

Unit 12, Cameron Court,
Winwick Quay,
Warrington WA2 8RF

T: 01925 820003

sales.warrington@ockwells.com

GLASGOW

Unit 2, 45 Mackellan Street,
Kinning Parkway Estate,
Glasgow G41 1RR

T: 0141 427 3366

sales.glasgow@ockwells.com

EAST LONDON

Unit E1, Thames View Business Centre
Fairview Industrial Park
Rainham RM13 8BT

T: 020 7473 8770

sales.rainham@ockwells.com